

TEKNİK DEĞERLER

PRODUCT SPECIFICATION

GRAMAJ (Gr/m²) (± %3) GRAMMAGE (Gr/m ²) (± %3)	280	300	320	350	380	400	420
KALINLIK (μ) MAX CALLIPER (μ) MIN. MAX.	430/440	450/460	470/480	530/540	560/580	600/610	630/640
PATLAMA (kPa) BURST STRENGTH (kPa)	260/280	270/300	310/320	330/340	330/340	340/350	350/370
COBB(gr/m²) COBB VALUE (gr/m ²)	390/410	400/410	400/420	410/430	420/430	410/430	410/440
NEM ± % 2 MOISTURE ± % 2	5	5	5	5	5	5	5
KOPMA TENSILE STRENGTH	4/6KG	4/9KG	5/11KG	6/12KG	7/13KG	7/13KG	8/14KG
SCOTT BOND (j/m²) SCOTT PLYBOND (j/m ²)	200-210	200-210	210-220	220-230	220-230	220-230	220-230
İÇERİK CONTENT	TAMAMEN ATIK KAGIT %100 WASTE PAPER						
EK ADDITIONAL	MAKSİMUM 2 EK MAXIMUM TWO ADDITIONS						
PAKETLER PACKETS	BOBİNLER SIKI SARILMIŞ, DÜZGÜN KESİLMİŞ, EKLER MUNTAZAM YAPILMIŞTIR. BOBINS TIGHTENED, STRAIGHTENED, APPENDICES ARE MADE REGULAR.						

ISO 10002:2018

ISO 45001:2018

ISO 14001:2015

ISO 9001:2015

Evrensekiz Beldesi Gündoğu Mah. Evrensekiz Caddesi No:1 Pk: 39790 Lüleburgaz/Kırklareli/Türkiye

T: +90 (288) 443 80 10 (7 Hat) (D:118) ,T: +90 (288) 443 80 19 www.koknar.com.tr